



# HPU 747 CLEAR VOC

## HIGH PERFORMANCE URETHANE TOPCOAT

ORIGINAL COLOR CHIPS CO - 26200 GROESBECK HWY - WARREN, MI



HPU 747 VOC is a two component polyester/aliphatic polyurethane coating that exhibits excellent characteristics for abrasion resistance, chemical resistance, flexibility, weathering, and UV stability. This product meets the VOC requirements for the newly enacted VOC laws of New York, Pennsylvania, New Jersey, Maryland, Connecticut, Massachusetts, California and other states as an industrial maintenance coating. It is recommended for auto service centers, warehouses, computer rooms, laboratories, aircraft hangers, cafeterias, exterior tanks, indoor or outdoor service and chemical exposures areas.

**SOLIDS BY WEIGHT:**

64% (clear) (+/- 2%)

**SOLIDS BY VOLUME:**

60% (clear) (+/- 2%)

**VOLATILE ORGANIC CONTENT:**

VOC content is less than 2.8 pounds per gallon (mixed)

**RECOMMENDED FILM THICKNESS:**

3-5 mils per coat wet thickness (yields 2-3 mils dry)

**COVERAGE PER GALLON:**

320 to 500 square feet @ 3-5 mils wet thickness

**PACKAGING INFORMATION:**

.75 gallon kit, 3 gallon and 15 gallon kits. 3 gal kit = 2 gallons part A (weight varies by color) and 1 gallon part B (8.5#) (weights and volumes approximate)

**MIX RATIO:**

2 parts A to 1 part B by volume (approximate)

**SHELF LIFE:**

1 year in unopened containers

**FINISH CHARACTERISTICS:**

high-gloss (>70 at 60 degrees @ Erichsen glossmeter)

**IMPACT RESISTANCE:**

Gardner Impact, direct & reverse=160 in lb (passed)

**ABRASION RESISTANCE:**

Taber abrasor CS-17 calibre wheel with 1000 gram total load and 500 cycles= 22.0 mg loss

**ADHESION:**

350 psi @ elcometer (concrete failure, no delamination)

**VISCOSITY:**

Mixed= 200-600 cps (typical)

**DOT CLASSIFICATIONS:**

Part A "FLAMMABLE LIQUID N.O.S., 3, UN1993, PGIII"  
Part B "FLAMMABLE LIQUID N.O.S., 3, UN1993, PGIII"

**HARDNESS:**

Shore D= 62

**FLEXIBILITY:**

No cracks on a 1/8" mandrel

**CURE SCHEDULE: (70°F)**

pot life – (1 1/2 gallon volume).....2-4 hours  
tack free (dry to touch).....3-5 hours  
recoat or topcoat.....5-9 hours  
light foot traffic.....14-24 hours  
full cure (heavy traffic).....3-5 days

**APPLICATION TEMPERATURE:**

45-90 degrees F.

**CHEMICAL RESISTANCE:**

REAGENT	RATING
acetic acid 5%	B
xylene	D
mek	A
methyl alcohol	B
gasoline	D
10% sodium hydroxide	E
50% sodium hydroxide	D
10% sulfuric	D
10% hydrochloric acid	C
20% nitric acid	B
ethylene glycol	D

Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: extensive chemical resistance information is available through your sales representative.

**PRIMER:**

Recommend, Urethane is designed as a topcoat but not directly to concrete. For best results primer with epoxy.

**TOPCOAT:**

None recommended

**LIMITATIONS:**

- \*Colors or clarity for clear may be affected by high humidity, low temperatures, or chemical exposure.
- \*For best results use a high quality 3/8" nap roller.
- \*Slab on grade requires moisture barrier.
- \*Substrate temperature must be 5°F above dew point.
- \*All new concrete must be cured for at least 30 days.
- \*Colored Version of HPU that are Light or bright colors (white, safety yellow, etc.) may require multiple coats or a suitable color coordinated primer to achieve a satisfactory hide.
- \*Colors may vary from batch to batch, therefore, use only product from the same batch for an entire job.



# HPH CLEARCOAT

## APPLICATION INSTRUCTIONS

**PRODUCT STORAGE:** Store product in an area as to bring the material to normal room temperature before using. Continuous storage should be between 60 and 90 degrees F.

**SURFACE PREPARATION:** Surface preparation will vary according to the type of complete system to be applied. For a one or two coat thin build system (3-10 mils dry) we recommend either mechanical scarification or acid etching until a suitable profile is achieved. For a complete system build higher than 10 mils dry, we recommend a fine brush blast (shot blast) All dirt, oil, dust, foreign contaminants and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause disbonding.

**PRODUCT MIXING:** This product has a two to one mix ratio by volume- merely mix two gallons of part A with 1 gallon part B. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. Avoid whipping air into the coating. Improper mixing may result in product failure.

**PRODUCT APPLICATION:** The mixed material can be applied by brush or roller. Maintain temperatures within the recommended ranges during the application and curing process. Properly prime the substrate. It is best to maintain a wet edge to avoid roller marks. Direct sunlight or high temperatures may cause visible roller marking during application. Too thick of an application may result in product failure. Exposure to certain types of lighting such as sodium vapor lights may cause the product to discolor. **It is critical to use ONLY with adequate ventilation, trapping the flammable vapors can cause product failure. After the material is rolled out make sure you have good air flow, placing a fan in the room blowing the solvent fumes out of area is essential. This will allow the material to cure properly.**

**RECOAT OR TOPCOATING:** Multiple coats of this product are acceptable. If you opt to recoat this product, you must first be sure that all of the solvents have evaporated from the coating during the curing process. The information on the front side are reliable guidelines to follow. However, it is best to test the coating before recoating or topcoating. This can be done by pressing on the coating with your thumb to verify that no fingerprint impression is left. If no impression is created, then the recoat can be started. Always remember that colder temperatures will require more cure time for the product before recoating can commence. Before recoating or topcoating, check the coating to insure no contaminants exist. If a blush or contaminants are present on a previous coat, remove with a standard detergent cleaner. When recoating this product with subsequent coats of the urethane, it is advisable to apply the recoat before 24 hours passes. Also, it is advisable to degloss the previous coat to insure a trouble free bond. You can also tack-rag the floor for best possible results. Basically what you'll want to do is degloss the urethane coating by light sanding, then use a rag dipped in thinner (m.e.k., Xylol Xylene, etc) (call tack ragging) and rub over the entire surface and allow to evaporate. This will soften up the coating and allow the subsequent urethane coating to adhere properly

**CLEANUP:** Use ketone solvents

**FLOOR CLEANING:** Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

**RESTRICTIONS:** Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle.



**DANGER! FLAMMABLE LIQUID AND VAPOR. HARMFUL OR FATAL IF SWALLOWED. ASPIRATION HAZARD - CAN ENTER LUNGS AND CAUSE DAMAGE. HARMFUL IF INHALED. MAY CAUSE CENTRAL NERVOUS SYSTEM EFFECTS, INCLUDING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN AND RESPIRATORY TRACT IRRITATION. MAY CAUSE ALLERGIC SKIN AND RESPIRATORY REACTION. OVEREXPOSURE MAY CAUSE BLOOD, LIVER, KIDNEY DAMAGE. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN. ORGANIC VAPOR RESPIRATOR MASK RECOMMENDED WHEN USING THIS PRODUCT.**

#### NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

*We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Listed physical properties are typical and should not be construed as specifications. NO WARRANTY IS MADE, EXPRESSED, OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sales of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW THE PRECAUTIONS TO PREVENT BODILY HARM.*